



## TECHNICAL INFORMATION SHEET

### STAY SILV® 35 BRAZING FILLER METAL

#### CHEMICAL COMPOSITION %:

Silver	35-36
Zinc	19-23
Copper	25-27
Cadmium	17-19
Other (Total)	0.15

#### PHYSICAL PROPERTIES:

Solidus 1125°F (607°C)  
Liquidus 1295°F (700°C)  
Density 4.84 troy ounces per cu.in.  
Electrical Conductivity 27.5 IACS

#### BRAZING PROPERTIES:

While fluid at temperatures above its liquidus, Stay Silv 35 offers a melting range suitable for filling wider clearances. It provides excellent joint strength and ductility. It is typically used to braze steel and dissimilar metal connections, such as copper or brass to various steel alloys. A uniform clearance of 0.002" – 0.005" is recommended for best capillary action.

Stay Silv 35 can be a acceptable choice for applications where sufficient fume ventilation/exhaust equipment is in place to assure operators are not exposed to cadmium oxide fume.

#### AVAILABLE FORMS

Standard wire diameters in coils and rods, and wound on spools.

#### SPECIFICATION COMPLIANCE:

ANSI/AWS A5.8 Class BA<sub>g</sub>-2, ASME SFA5.8 Class BA<sub>g</sub>-2, QQ-B-654A Grade VIII

#### RECOMMENDED FLUX:

Stay-Silv® white flux is suitable for many applications. Stay-Silv® black brazing flux is often used to braze stainless steel or where heating cycles are prolonged or heat is focused as in induction brazing.

#### SAFETY INFORMATION:

**WARNING: PROTECT yourself and others. Read and understand this information.**

**CONTAINS CADMIUM – FUMES ARE POISONOUS AND CAN KILL – DO NOT BREATH FUMES. EVEN BRIEF EXPOSURE TO HIGH CONCENTRATIONS SHOULD BE AVOIDED.**

**HEAT RAYS, (infrared radiation) from flame or hot metal can injure eyes.**

- Before use, read and understand the manufacturer's instructions, Material Safety Data Sheets (MSDS), and your employer's safety practices.
- Keep your head out of fumes.
- Use enough ventilation, exhaust at the flame, or heat source, to keep fumes and gases from your breathing zone and the general area.
- Wear correct eye, ear, and body protection.
- See American National Standard Z49.1, *Safety in Welding, Cutting, and Allied Processes*, published by the American Welding Society, 8669 Doral Blvd., Doral, Florida 33166; OSHA Safety and Health Standards, available from the U.S. Government Office, Washington, DC 20402.

#### STATEMENT OF LIABILITY- DISCLAIMER:

Any suggestion of product applications or results is given without representation or warranty, either expressed or implied. Without exception or limitation, there are no warranties of merchantability or of fitness for particular purpose or application. The user must fully evaluate every process and application in all aspects, including suitability, compliance with applicable law and non-infringement of the rights of others. The Harris Products Group and its affiliates shall have no liability in respect thereof.

#### THE HARRIS PRODUCTS GROUP

A LINCOLN ELECTRIC COMPANY



4501 Quality Place • Mason, OH 45040 U.S.A Tel: 513-754-2000 Fax: 513-754-6015  
Additional information available at our web site: [www.harrisproductsgroup.com](http://www.harrisproductsgroup.com)